



# AUBE00049 Berger Everlast Interior Low Sheen

#### Introduction

Part A

668-line

#### **Description and Image**

Berger Everlast Low Sheen creates a beautiful and washable finish that is built to last in your home. Featuring low VOC, low odour BreatheEasy® technology, Berger Everlast allows you to move back into your home sooner. Its smooth finish is tough, hardwearing, and designed to last.



## Features and Benefits

- Water based
- Excellent stain resistance
- Excellent mould resistance
- Low odour, low VOC BreatheEasy (R)
- Beautiful smooth and washable finish
- Tough and hardwearing

## Uses

Berger Everlast is ideal for all interior broadwall areas.

✓ Interior

Performance Guide	
Weather  Designed for interior use only.	Salt NA
Heat Resistance Softens and sticks to other painted surfaces over 70°	Water Suitable for use in wet areas
Solvent Sensitive to aromatic hydrocarbons and alcohols	Abrasion Good wet and dry burnish resistance and stain removal
Acid NA	Alkali <b>NA</b>





Typical Properties					
Gloss Level Low Sheen		Thinner <b>Water</b>			
Colour Machine tinted to a wide range of	colours from white, deep, extra de	ep, extra bright and coloured bases.			
Components 1		Number of Coats 2			
Toxicity NA		V.O.C. Level < 5g/L untinted			
Shelf Life 2 years		Meets GBCA V.O.C. Requirements? Yes Total Volatile Organic Content (TVOC accordance to the stated methodolog Manuals. The TVOC content is theore of the known VOC values of the prod These materials include the base pair required for non-factory packaged co	gy within Green Star Technical etically calculated as the sum total uct's raw material components. It plus additional low VOC tinter		
Touch Dry 30 minutes					
Clean Up					
₩ater					
Clean Up Description Clean all equipment immediately wi	th water.				
Application Methods					
Air Spray 🛉 Airless	Spray 🕴 Brush 🚏 Rol	ler			
Application Conditions	Solids by Volume				
	40				
	Min	Max	Recommended		
Wet Film Per Coat (microns)			62.5		
Dry Film Per Coat (microns)			25		
Recoat Time (min/hours)	2 hr	Indefinite	2 hr		
Theoretical Spread Rate (m²/L)			16.00		





#### **Application Guide**

Surface Preparation

• Do not apply paint if the temperature is below 10°C or likely to fall below 10°C during the drying period.

#### Preparation

Scrape off loose and flaking paint. Wash with sugar soap and rinse clean. Fill nail holes, cracks, etc. with a suitable filler. Sand smooth and dust down Sand gloss and semi gloss surfaces to a matt finish before painting.

#### Previously painted surface - Undercoat

Not required.

#### Bare plasterboard, cement or brick - Undercoat

Berger Triple Prep® Acrylic Sealer Undercoat.

#### Bare set plaster or powdery surfaces - Undercoat

Berger Triple Prep Oil Based.

#### Bare timber - Undercoat

Berger Triple Prep Acrylic.

#### Over enamel paint - Undercoat

Not required.

Application Procedure and Equipment

Stir well before use with a broad, flat stirrer. Under hot weather conditions use a hot weather additive or thin using 100mL of clean water per litre if required.

#### Application

After following the preparation guide, apply with brush, spray or medium nap roller (9-12mm). Application should be in standard temperature conditions (above 10°C and below 30°C). Apply 2 coats of Berger Everlast Low Sheen. To achieve the best finish, ensure the paint is not worked excessively. When coating over some dark colours an extra coat may be required. Thinning not usually required. If necessary thin with up to 100 ml of water per litre to ease application.

Airless/Conventional Spray: Suitable for application by all standard spray equipment. For conventional spraying up to 125 ml per litre of water may be added to aid atomisation. For airless spraying up to 30 ml per litre of water may be added to aid atomisation.

#### Care of new paintwork

Avoid exposure to steam and condensation for 48 hours after painting. May be cleaned with a wet cloth and detergent after 7 days.

#### Drvina time

Drying times on a day of around 25°C. Touch dry in 30 minutes. Re-coat in 2 hours. Under cooler or humid conditions allow longer times.





Transport and Storage		
Pack A 668-LINE		
Size:	Weight:	
1Litre 2Litre 4 Litre 10 Litre 15 Litre	1.5Kg 3.5Kg 5.6Kg 14.0Kg 21.	7Kg
Flash Point		UN N
NA		NA

#### Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from <a href="www.duspecplus.com.au">www.duspecplus.com.au</a>. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.