



# **AUBE00234 Berger Everlast Interior Matt**

Part A

62A - Line

Introduction

### Description and Image

Berger Everlast creates a beautiful and washable finish that is built to last in your home. With a low VOC and low odour formulation, Berger Everlast is Breathe Easy® allowing you to move back into your home sooner. Its smooth finish is tough, hard wearing and designed to last.

### **Features and Benefits**

- Tough and hard wearing
- Excellent stain resistance
- Excellent mould resistance
- Beautiful smooth and washable finish

#### Uses

Kitchen, Bathroom, Bedroom, Living, Laundry

Interior

### **Precautions and Limitations**

All preparation and painting must conform to AS2311: The Painting of Buildings. Do not paint at temperatures below 10°C or when the temperature of surface may fall below 10°C during the drying period. Avoid exposure to steam and condensation for 48 hours after application. Although film is dry to touch in 30 minutes, allow 7 days for film to fully cure before cleaning with a cloth, or soft brush wet with detergent solution.

Tinted colours. Ensure that paint is thoroughly shaken and stirred immediately after addition of tinter to can and again before use. Darker colours will show more signs of marking and scuffing than lighter colours - if you are considering using a dark colour in a high traffic area you may want to consider a higher sheen level or the use of a protective clear coat.

Performance Guide	
Weather Designed for interior use only.	
Heat Resistance Softens and sticks to other painted surfaces over 70C	Water Not recommended for high steam and condensation areas.
Solvent Sensitive to aromatic hydrocarbons and alcohols	





Typical Properties					
Gloss Level 2-5 at 60 degrees		Thinner Water			
Colour Tinted to a wide range of colours from white					
Number of Coats 2*					
Toxicity Lead free. Dry film is non-toxic.		V.O.C. Level			
Touch Dry 30 mins					
Clean Up					
Water					
Clean Up Description Clean all equipment with water					
Application Methods					
Air Spray 🛉 Airless Spray 📍 Brush 🚏 Roller					
Application Conditions	Solids by Volume				
	32.7				
	Min	Max	Recommended		
Wet Film Per Coat (microns)			63		
Dry Film Per Coat (microns)			21		
Recoat Time (min/hours)	2 hours	Indefinite			
Theoretical Spread Rate (m²/L)			16		





## **Application Guide**

Surface Preparation

• Do not apply paint if the temperature is below 10°C or likely to fall below 10°C during the drying period.

All surfaces must be thoroughly cleaned and free of all loose dirt, dust, grease, loose or flaking paint, and loose surface plaster. Efflorescence or mould on masonry or concrete surfaces must be treated. Flatten gloss surfaces by thoroughly sanding and wipe clean with a damp cloth, then apply primer, sealer or undercoat as required. Do not sand between coats.

Application Procedure and Equipment

\*Some colours may require more than the recommended number of coats to achieve full opacity.

#### Brush, roller and spray.

Stir contents thoroughly before and during use with a broad flat stirrer using an upward lifting action.

#### Brush/Roller:

Use medium nap roller. Pre wet brushes and roller with water before commencing application. Avoid excessive brushing or rolling back into the paint which has been drying for more than 3 minutes. Thinning not usually required. Under hot conditions upto 50ml per litre of water may be used.

#### Airless/Conventional Spray:

Suitable for application by all standard spray equipment. If necessary, to aid atomisation, up to 100 ml/litre water may be added for conventional spray or up to 30 ml/litre of water for airless spray.

Health and Safety			
SDS Number DLXGHSEN002746	SDS Link View SDS Link		
Personal Equipment  Wear eye protection and when spraying wear a dust mask			
Please refer to SDS Link. In case of emergency, please call 1800 220 770.			

Transport and Storage		
Pack A 62A - Line		
Size:	Weight:	
1, 4, 10, 15 Litre	1.47Kg, 5.55kg, 13.7kg, 21.1Kg	
Flash Point		UN Number
NA		NA
Dangerous Goods Class		
NA		





#### Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from <a href="www.duspecplus.com.au">www.duspecplus.com.au</a>. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.