

AUDU00032 Dulux Texture Medium

Introduction

Part A
195-85715

Approvals
NA

Description and Image

Dulux Medium Texture is a sandy bagged texture designed to modernise brick, masonry and fibre cement surfaces.

Features and Benefits

- Water based
- High build 100% Acrylic paint
- Easy application
- Bagged texture finish
- Same day recoat and clean up
- Proven durability at high film builds
- Achieves texture finish without special training
- Low cost alternative to traditional rendering and texturing methods

Uses

Dulux Medium Texture is a 100% acrylic texture paint for direct application to bricks, concrete, fibrocement and masonry. Formulated to create a tough, flexible, high build bagged texture finish that modernises brick and masonry surfaces.

Precautions and Limitations

All preparation and painting must conform to AS2311: The Painting of Buildings.

Do not apply at temperatures below 10C or when the temperature may fall below 10C during the drying period. In summer, paint on the shady side of the building. Do not apply during hot and windy conditions. Protect from rain for 24 hours after application.

Performance Guide

Weather

Excellent resistance to weathering with minimal colour change and dirt pick up.

Heat Resistance

Softens and suffers from dirt pick up over 70 degrees.

Water



Resists prolonged rain and condensation.

Solvent

Sensitive to aromatic hydrocarbons and alcohols.

Abrasion

Good resistance to abrasion.

Typical Properties			
Gloss Level 0-5 at 60 degrees	Thinner Water		
Colour Can be tinted to a wide range of pastel and medium depth colours.			
Components 1			
Toxicity Lead free. Dry film is non-toxic.	V.O.C. Level < 60g/L untinted		
Touch Dry 1 hour			
Clean Up  Water			
Clean Up Description Clean all equipment with water			
Application Methods  Roller			
Application Conditions	Solids by Volume		
	<input type="text" value="53"/>		
	Min	Max	Recommended
Wet Film Per Coat (microns)	<input type="text" value="358"/>	<input type="text" value="358"/>	<input type="text" value="358"/>
Dry Film Per Coat (microns)	<input type="text" value="190"/>	<input type="text" value="190"/>	<input type="text" value="190"/>
Recoat Time (min/hours)	<input type="text" value="4 Hours"/>	<input type="text" value="Indefinite"/>	<input type="text"/>
Theoretical Spread Rate (m ² /L)	<input type="text" value="2.8"/>	<input type="text" value="2.8"/>	<input type="text" value="2.8"/>

Application Guide

Surface Preparation

All surfaces must be thoroughly cleaned and free of all dirt, loose and flaking paint. Efflorescence or mould must be treated before application of paint. New concrete, mortar or cement render must be allowed to cure for 4 to 8 weeks depending on concrete thickness and drying conditions. Fill holes with grouting cement. Wash down with water using a stiff brush to remove all loose material.

To test the adhesion of previously painted surfaces, cut an 'X' through the existing paint with a sharp blade, press cellulose tape firmly across the cut and then rip the tape off. If the old paint or render comes off, it should be removed.

On porous surfaces, applying a priming coat of Dulux Texture Primer will condition the surface and help aid application of additional coats.

Application Procedure and Equipment

Long Nap Roller (12mm recommended) and sponge or mitt

Delivery: generously load the roller and apply from the ground upwards in vertical strips of 1/2 to 1 metre lengths. Reload the roller after each strip and repeat until 3 or 4 strips are applied. Even out material by rolling diagonally across the surface. It is important to work swiftly to allow time for the finishing process and this can be best achieved by working in a team, with one "delivering" and the other "finishing".

Finishing: working with a clean bucket of water and a sponge (we recommend a fine cell sponge) or mitt, wet the sponge or mitt and, working in a circular motion, sponge finish the applied material to obliterate the roller pattern, fill mortar joints and/or cover surface imperfections. Clean out the sponge in the water and lightly finish in larger circular strokes. Depending upon the finishing pressure and material retained from the sponge, varied finishing effects can be achieved, from a light "mottled" effect to a more prominent "swirl" pattern.

Stir contents thoroughly before and during use with a broad flat paddle, using an up and down scooping action.

Application is in 2 parts: Delivery (via a roller) and Finishing (using a sponge, brush or mitt)

Repeat the above delivery and finishing procedure, maintaining a working wet edge, until completed.

2 coats are recommended but additional coats may be required depending upon the depth of the mortar joints.

Health and Safety

SDS Number
20366, 0

SDS Link
[View SDS Link](#)

Please refer to SDS Link. In case of emergency, please call 1800 220 770.

Transport and Storage

Pack A
195-85715

Size:

10 litre

Weight:

15.5 Kg

Flash Point

NA

UN Number

NA

Dangerous Goods Class

NA

Package Group

NA

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.